



Standard: **EN 1706 ALUMINUM AND ALUMINUM ALLOYS CASTINGS**  
**EN 1676 ALUMINUM ALLOYED INGOTS FOR REMELTING**

Alloy group: **Al Si 5 Mg**

Alloy designation: **EN AB and AC 45300 - Al Si 5 Cu 1 Mg**

Replaces: **UNI 3600 - G Al Si 5 Cu Mg**

#### CHEMICAL COMPOSITION %

ALLOY		ELEMENTS												
		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Pb	Sn	Ti	Individual impurities	Global impurities
EN AB 45300	min	4,5		1,0		0,40								
	max	5,5	0,55	1,5	0,55	0,65	-	0,25	0,15	0,15	0,05	0,20	0,05	0,15
UNI 3600 - G Al Si 5 Cu Mg	min	4,5		1,10		0,45								
	max	5,5	0,5	1,50	0,1	0,65	-	0,10	0,05			0,15		0,15

#### MECHANICAL FEATURES DETECTED FROM SEPARATE CASTING TEST SPECIMENS

Casting process	Temper designations	Rm Tensile strenght		Sp 0,2 Proof Stress		A Elongation		HB Brinell hardness	
		EN 1706	UNI 3600	EN 1706	UNI 3600	EN 1706	UNI 3600	EN 1706	UNI 3600
		Mpa	N/mm2	Mpa	N/mm2	%	%	HBW	HB
SAND (as cast)	F		145-175		125-145		1-2		65-85
	T4	170	215-245	120	155-185	2	2-3	80	85-100
	T6 2	230	245-265	200	185-215	1	1-2	100	95-110
CHILL (as cast)	F		205-245		125-155		4-5		70-95
	T4	230	305-345	140	195-235	3	5-9	85	100-130
	T6 3	280	345-390	210	275-315	1	2-5	110	110-140

Merkez Ofis/Head Office : Baksav San.Sit Mustafa Kurdođlu Cad. no:22/2 Beylikdüzü/İSTANBUL/TURKEY  
 Fabrika/Factory : Mimarşinan Mah. Eski Bağlar Cad. No:23 Kapaklı - Çerkezköy / Tekirdađ/TURKEY

Tel/Phone : +90 212 875 22 22  
 Faks/Fax : +90 212 875 99 83  
 E-posta/E-mail : info@mesek.com.tr